



Attachment no. 1 to the certificate of analysis for work order PR2019636

RESULTS OF GRAIN SIZE ANALYSIS

Sample label:	N00722785		
Lab. ID:	001		
Total weight of sample:	[g]	131.13	
q	< 0.002 mm	[%]	0.10
q	0.002–0.004 mm	[%]	0.23
q	0.004–0.008 mm	[%]	0.41
q	0.008–0.016 mm	[%]	0.54
q	0.016–0.032 mm	[%]	0.73
q	0.032–0.063 mm	[%]	0.80
q	< 0.063 mm	[%]	2.81
q	0.063–0.125 mm	[%]	1.60
q	0.125–0.250 mm	[%]	4.78
q	0.250–0.500 mm	[%]	25.42
q	0.500–1.000 mm	[%]	39.56
q	1.000–2.000 mm	[%]	20.83
q	2.000–4.000 mm	[%]	4.04
q	4.000–8.000 mm	[%]	0.96
q	8.000–16.000 mm	[%]	0.00
q	16.00–31.50 mm	[%]	0.00
q	31.50–63.00 mm	[%]	0.00
q	> 63.00 mm	[%]	0.00
Q	< 0.002 mm	[%]	0.10
Q	< 0.004 mm	[%]	0.33
Q	< 0.008 mm	[%]	0.74
Q	< 0.016 mm	[%]	1.27
Q	< 0.032 mm	[%]	2.00
Q	< 0.063 mm	[%]	2.81
Q	< 0.125 mm	[%]	4.41
Q	< 0.250 mm	[%]	9.18
Q	< 0.500 mm	[%]	34.61
Q	< 1.000 mm	[%]	74.16
Q	< 2.000 mm	[%]	95.00
Q	< 4.000 mm	[%]	99.04
Q	< 8.000 mm	[%]	100.00
Q	< 16.00 mm	[%]	100.00
Q	< 31.50 mm	[%]	100.00
Q	< 63.000 mm	[%]	100.00

q –fraction percentage part, Q – fraction cumulative part.

Test method specification: CZ_SOP_D06_07_120 Grain size analysis using the wet sieve analysis using laser diffraction (fraction from 2 µm to 63 mm). Fractions > 63 mm, 31.5–63 mm, 16–31.5 mm, 8–16 mm, 4–8 mm, 2–4 mm, 1–2 mm, 0.5–1 mm, 0.25–0.50 mm, 0.125–0.25 mm and 0.063–0.125 mm were determined by wet sieving method, other fractions were determined from the fraction "<0.063 mm" by laser particle size analyzer using liquid dispersion mode.

Test specification, deviations, additions to or exclusions from the test specification:



RESULTS OF GRAIN SIZE ANALYSIS

